





ISO 9001:2008



REACH Status: Pre Registered

Date: 01.01.2018 Revision: 04


| D | r | n | Ч | ш | ī | r | ŀ | D | Δ | c | r | ri | in | ł | i | n | n | ١ |
|---|---|---|---|---|---|---|---|---|---|---|---|----|----|---|---|---|---|---|
| | | | | | | | | | | | | | | | | | | |

| CI Generic Name | Pigment Yellow 155 |
|-------------------|--------------------|
| CI No. | 200310 |
| EINECS No. | 271 – 176 - 6 |
| Molecular Formula | C34H32N6O12 |

| PIL Product Code | PRPL 1042T |
|------------------|---------------------|
| CAS No. | 68516 - 73 - 4 |
| Chemical Type | Bisacetoacetarylide |
| Molecular Weight | 716.65088 |

Chemical Name: tetramethyl 2,2'-[1,4-phenylenebis[imino(1-acetyl-2-oxoethane-1,2-diyl)azo]]bisterephthalate

| Physical Properties | |
|---------------------------|-------------|
| Sieve Residue (PPM) Max. | 1000 |
| Oil Absorption(gms) | |
| Bulk Density(gm/ml) | 0.15 – 0.30 |
| Salt Content (%) Max. | 1 |
| Moisture Content (%) Max. | 1 |
| PH Value | 6 - 8 |



| Fastness properties | | | | | | |
|---------------------|--------------|----------------|--|--|--|--|
| Heat °C | PP-Mass Tone | 200°C / 5 min. | | | | |
| Heat °C | PP-Tint Tone | 220°C / 5 min. | | | | |
| Light | Mass Tone | 8 | | | | |
| Light | Tint Tone | 7 -8 | | | | |
| Weather | Mass Tone | 3 | | | | |
| Weather | Tint Tone | - | | | | |
| Migration | | 3-4 | | | | |

| Specification | | | | | | | |
|------------------------------|--|--|--|--|--|--|--|
| Coloristic properties | Strength: ± 5 % | | | | | | |
| Coloristic properties | DA,DB,DE,DC,DH,DL: ± 1 | | | | | | |
| Light fastness : Scale 1-8 | 1~Poor & 8 ~ Excellent | | | | | | |
| Weather fastness : Scale 1-5 | 1~Poor & 5 ~ Excellent | | | | | | |
| Migration : Scale 1-5 | 1~Poor & 5 ~ Excellent | | | | | | |
| Heat Stability °C | DE≤ 3 at Maximum Temp with dwell time 5 minutes. | | | | | | |

Application

PO, Rubber, PVC, PS, PP fiber

The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Regd. Office: 601-602, Surya Rath, Panchvati, 1st. Lane, Opp. White House, Ambawadi, Ahmedabad-380 006, Gujarat, India